



Preliminary Product Data Sheet

IROPRINT F 90116

POLYESTER-BASED THERMOPLASTIC POLYURETHANE FILAMENT (TPU)

PRODUCT DESCRIPTION

IROPRINT F 90116 is a polyester-based Thermoplastic Polyurethane (TPU) for Fused Filament Fabrication (FFF). Key features are high elasticity, abrasion resistance, cut and scratch resistance and good low temperature performance. IROPRINT F 90116 is the fastest printing filament in our range.

MAIN APPLICATIONS

Footwear, hoses and gaskets, robotic grippers, seals and other applications that need to be soft and elastic, yet strong and tough.

TYPICAL PROPERTIES

| Properties | NORM | Value XY | Value Z | Unit |
|-------------------------------|------------|----------|---------|-------------------|
| Hardness (after 3 sec.) | ISO 7619 | 90 | | Shore A |
| Hardness (after 3 sec.) | ISO 7619 | 40 | | Shore D |
| Tensile strength | DIN 53504 | 36 | 20 | MPa |
| Elongation @ break | DIN 53504 | 550 | 350 | % |
| Abrasion | ISO 4649 | 43 | | mm ³ |
| Density | ISO 1183-1 | 1.170 | | g/cm ³ |
| Tear strength | ISO 34-1 | 114 | 47 | N/mm |
| Compression set at 70h @ 23°C | ASTM D 395 | 23 | | % |

| Print parameters | NORM | Value | Unit |
|-----------------------------|------|--------|------|
| Nozzle temperature | | 245 | °C |
| Bed temperature | | 20-80 | °C |
| Print speed | | 30-100 | mm/s |
| Extrusion multiplier (Flow) | | 1.8 | |
| Fan speed | | 100 | % |
| Nozzle diameter | | 0.4 | mm |



HEALTH & SAFETY ADVICE

Before undertaking any trials with this product, it is essential that all personnel are aware of the necessary precautions that must be taken. These are detailed in the relevant Safety Data Sheet, which will be provided by HUNTSMAN.

SUPPLY & STORAGE

Diameters: 1.75 mm \pm 0.05 mm
2.85 mm \pm 0.05 mm
Spool Size: 16 Spools per box, approximately 1 kg per spool. Other packaging types might be available on request.
Each spool is boxed individually, and vacuum packed with desiccant.

IROPRINT F 90116 has an expected shelf life of minimum 12 months after shipment date. The product should be stored in a dry and cool place in the manufacturer's original packaging.

MATERIAL PREPARATION

3 hours at 70–80 °C in dehumidified air.
Dew point: -30 °C

PHYSICAL FORM

Type: TPU Filament

Release date: October 3, 2019

For further information, please contact your nearest sales office: http://www.huntsman.com/PU_customer_service. While the information and recommendations in this publication are, to the best of our knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose. Nothing in this publication is to be construed as recommending the infringement of any patent or other intellectual property right, and no liability from such an infringement is assumed. Nothing in this publication is to be viewed as a license under any intellectual property right. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of Huntsman International LLC or of its affiliated companies. Huntsman Polyurethanes is an international business unit of Huntsman International LLC. Huntsman Polyurethanes trades through Huntsman affiliated companies in different countries such as Huntsman International LLC in the USA and Huntsman Holland BV in Western Europe.